

5/8" Struct 1 MDO Plyform

Produced at our Rogue River, OR facility, Murphy's 5/8" Struct 1 MDO plyform is for concrete forming applications. Struct 1 MDO is perfect for projects requiring exposed concrete with a consistent, smooth surface.

High manufacturing standards and leading concrete panel technology create a panel with high performance characteristics. When properly used and maintained, our MDO panels will increase the number of pours per panel over standard plywood, thus reducing per pour costs.

Murphy 5/8" MDO is manufactured with durable, quality Douglas fir veneers. An industry standard, 35% resin content MDO (medium density overlay) layer is applied to one side. The panels have a facility-applied Nox-Crete™ release agent and the edges are sealed with top-of-the-line Willamette Valley Form Seal to prevent moisture contamination.

STRUCT 1 MDO FEATURES

A resin-impregnated fiber overlay (MDO) is bonded to the face veneer of the panel. This particular overlay results in a superior matte finish, when a glossy finish is undesirable and a final finish of paint or acoustic texture might be specified.

Struct 1 MDO's matte surface also helps hold release agents uniformly to reduce blotchiness from uneven hydration. Additionally, it has improved chemical resistance and better form oil retention for easier cleanup.

Murphy applies a release agent as part of the panel manufacturing process. Additionally, the panel edges are sealed with a specially formulated sealer to resist water, alkali and sunlight exposure. The overall result is a more durable and cost effective panel than traditional BB concrete form.

GREEN AND CERTIFIED

The glue used to manufacture Murphy's 5/8" Struct 1 MDO panels is APA certified and safe for both suppliers and builders.

Panels manufactured in accordance with the Engineered Wood Association PS 1 standard use phenol formaldehyde, a waterproof adhesive that is highly durable and stable resulting in low formaldehyde emissions.

APA rated panels use moisture resistant adhesives that are exempt from U.S. HUD and California formaldehyde regulations due to these very low emissions.

Please ask us about our engineered concrete form products including scaffold plank and concrete form beams.



SPECIFICATIONS

Description: One side MDO BCX Structural 1 Concrete Form

Size: 48" X 96" + 0, - 1/16"

Thickness: 5/8"

Construction: 5 ply Douglas fir

Overlay: 35% resin content MDO

Edge Seal: Willamette Valley Form Seal (Gray #15)

Release Agent: Nox-Crete™ Form Coating E

* Panels meet APA PS1-19 specifications

Specifications subject to change without notice

5/8" Struct 1 Allowable Stress Design Load Capacities (lbs/ft ²)				
Support Spacing (in.)	Face Grain Across Supports		Face Grain Parallel Supports	
	5/8		5/8	
Size	5/8		5/8	
Deflection	<u>L/270</u>	<u>L/360</u>	<u>L/270</u>	<u>L/360</u>
4.0	5140	5140	2890	2890
8.0	1870	1870	1065	1065
12.0	830	830	450	340
16.0	465	390	190	140
19.2	305	230	135	100
24.0	160	120	-	-
Source: APA Engineer Calculations				
* Cells with dashes have pressures less than 100 psf.				

CARE AND HANDLING

Preparation:

MDO panels are edge sealed at the mill with a high quality, water based coating. During form work construction, plywood edges are often exposed by sawing and drilling. These edges should be sealed. This slows down the penetration of water which can cause panel swelling, edge failure, and staining.

Stripping:

Metal bars or pry bars should not be used on plywood because they will damage the panel surface and edge. Use wood wedges, tapping gradually when necessary.

Cleaning and Release Agent Application:

Soon after removal, plywood forms should be inspected for wear, cleaned, repaired, refinished and lightly treated with a form-release agent before reusing. Use a hardwood wedge and a stiff fiber brush for cleaning (a metal brush may cause wood fibers to "wool"). Light tapping on the backside with a hammer will generally remove hard scale concrete. Tie holes may be patched with metal plates, plugs or plastic materials. Nails should be removed and holes filled with patching plaster, plastic wood, or other patching material.

Handling and Storage:

Care should be exercised to prevent panel chipping, denting and corner damage during handling. Panels should never be dropped. The forms should be carefully piled flat, face to face and back to back, for hauling. Forms should be cleaned immediately after stripping and can be solid-stacked or stacked in small packages, with faces together. Panels should be stored on a dry level surface away from direct sunlight.



MURPHY
Softwood Plywood

2350 Prairie Road
Eugene, OR
97402

OFFICE 541.461.4545
FAX 541.461.4546
www.murphyplywood.com